

Site Occupancies, VUV-UV-vis Photoluminescence, and X-ray Radioluminescence of Eu²⁺-Doped RbBaPO₄

Zhou, Rongfu; Ma, Fengkai; Su, Fang; Ou, Yiyi; Qi, Zeming; Zhang, Jianhui; Huang, Yan; Dorenbos, Pieter; Liang, Hongbin

DOI

[10.1021/acs.inorgchem.0c02714](https://doi.org/10.1021/acs.inorgchem.0c02714)

Publication date

2020

Document Version

Accepted author manuscript

Published in

Inorganic Chemistry

Citation (APA)

Zhou, R., Ma, F., Su, F., Ou, Y., Qi, Z., Zhang, J., Huang, Y., Dorenbos, P., & Liang, H. (2020). Site Occupancies, VUV-UV-vis Photoluminescence, and X-ray Radioluminescence of Eu²⁺-Doped RbBaPO₄. *Inorganic Chemistry*, 59(23), 17421-17429. <https://doi.org/10.1021/acs.inorgchem.0c02714>

Important note

To cite this publication, please use the final published version (if applicable).
Please check the document version above.

Copyright

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights.
We will remove access to the work immediately and investigate your claim.

Site occupancies, VUV-UV-vis photoluminescence and X-ray radioluminescence of Eu^{2+} doped RbBaPO_4

Rongfu Zhou^a, *Fengkai Ma*^a, *Fang Su*^a, *Yiyi Ou*^a, *Zeming Qi*^b, *Jianhui Zhang*^a, *Yan Huang*^c,
Pieter Dorenbos^d, *Hongbin Liang*^{a, *}

^a MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

^b National Synchrotron Radiation Laboratory, University of Science and Technology of China, Hefei 230029, P. R. China

^c Beijing Synchrotron Radiation Facility, Institute of High Energy Physics, Chinese Academy of Sciences, Beijing 100039, P. R. China

^d Faculty of Applied Sciences, Delft University of Technology, Mekelweg 15, 2629 JB Delft, The Netherlands

ABSTRACT: RbBaPO_4 : Eu^{2+} phosphors have been prepared by a high-temperature solid-state reaction method, and the structure was determined by Rietveld refinement based on powder X-ray diffraction (P-XRD) data. Their VUV-UV-vis photoluminescence properties are systematically

investigated with three objectives: (1) based on low-temperature spectra, we clarify the site occupancies of Eu^{2+} , and demonstrate that the doublet emission bands at ~ 406 and ~ 431 nm are originated from Eu^{2+} in Ba^{2+} [$\text{Eu}^{2+}(\text{I})$] and Rb^+ [$\text{Eu}^{2+}(\text{II})$] sites, respectively; (2) an electron-vibrational interaction (EVI) analysis is conducted to estimate the Huang-Rhys factors, the zero-phonon lines (ZPLs) and the Stokes shifts of Eu^{2+} in Rb^+ and Ba^{2+} sites; (3) the studies on luminescence decay of $\text{Eu}^{2+}(\text{I})$ reveal that dipole-dipole interaction is mainly responsible for the energy transfer from $\text{Eu}^{2+}(\text{I})$ to $\text{Eu}^{2+}(\text{II})$, and the energy migration between $\text{Eu}^{2+}(\text{I})$ is weak. Finally, the X-ray excited luminescence (XEL) spectrum indicates that the light yield of the sample $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ is ~ 17700 ph/MeV, showing its potential application in X-ray detecting.

1. INTRODUCTION

Eu^{2+} is one of the lanthanide ions and has $4f^7$ electronic configuration. It shows 5d-4f emission when the lowest $4f^65d$ state is located below the $^6\text{P}_J$ level, and has been extensively studied for applications in lighting, display and scintillation detection. $\text{BaMgAl}_{10}\text{O}_{17}:\text{Eu}^{2+}$ has been a suitable blue-emitting phosphor in tricolor lamps for years, $\text{BaFCl}:\text{Eu}^{2+}$ is the first commercially available rare-earth X-ray phosphor, $\text{SrAl}_2\text{O}_4:\text{Eu}^{2+}$, Dy^{3+} is a long phosphorescent phosphor with high brightness and is widely applied, $\text{SrI}_2:\text{Eu}^{2+}$ is a scintillator with high light output for detecting ionizing radiation, and $\text{Sr}[\text{LiAl}_3\text{N}_4]:\text{Eu}^{2+}$ is considered to be a potential red-emitting phosphor for next-generation high-power phosphor-converted white-light-emitting diodes.¹⁻⁴

The following aspects are essential for the development of novel Eu^{2+} doped luminescent materials. Firstly, the site occupancy of the doping lanthanide ion must be clarified, because it is one of the most crucial factors for the excitation and emission wavelengths of Eu^{2+} in a specific host compound.^{5,6} For instance, the excitation peaks of Eu^{2+} in the ten-fold coordinated Sr^{2+} site and six-fold coordinated Ca^{2+} site of $\text{Li}_4\text{SrCa}(\text{SiO}_4)_2$ are found at ~ 290 and ~ 375 nm, respectively.⁷

The emission bands at ~472, ~445 and ~406 nm are assigned to Eu^{2+} at Sr(I)O_9 , Sr(III)O_8 and Sr(II)O_7 polyhedral sites in $\text{Sr}_5\text{SiO}_4\text{Cl}_6$, respectively.⁸ The blue emission peaking at 471 nm is originated from the occupancies of Eu^{2+} in the monovalent cation sites Rb^+ , Na^+ and Na^{2+} in $\text{RbNa}_3(\text{Li}_3\text{SiO}_4)_4$.⁹ Eu^{2+} occupies into the LuO_6 and K_2O_6 polyhedrons in $\text{K}_3\text{LuSi}_2\text{O}_7$ with deep red emissions.¹⁰ Secondly, the electron-vibrational interaction (EVI) is another important factor for the luminescence properties of rare earth ions. It has significant influence on the position and the width of the emission band of Eu^{2+} .¹¹⁻¹³ Thirdly, the investigations on the energy-transfer dynamics through fluorescence decays are beneficial to understand the luminescence processes.^{14,15}

The compound RbBaPO_4 belongs to ABPO_4 (A is an alkali metal, B is an alkali earth metal) type orthophosphates, it has good thermal, hydrolytic stability and wide band gap.¹⁶⁻²¹ On the basis of systematic studies on the VUV-UV-vis photoluminescence and X-ray radioluminescence of Eu^{2+} doped RbBaPO_4 , in this paper we report a potential X-ray phosphor $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ after discussions on the site occupancies, the EVI and the energy-transfer dynamics in detail.

2. EXPERIMENTAL SECTION

2.1. Preparation. The pure host compound and Eu^{2+} -doped RbBaPO_4 samples were prepared using a conventional solid-state reaction route at high-temperature. The analytic reagents BaCO_3 , Rb_2CO_3 , $(\text{NH}_4)\text{H}_2\text{PO}_4$, and 99.99% pure rare-earth oxides Eu_2O_3 were used as starting materials. The reactants were weighed with nominal formulas $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ and ground thoroughly in an agate mortar. The mixtures were moved to alumina crucibles and pre-fired at 975 K in air atmosphere for 3 h. Then Eu^{2+} doped samples were annealed at 1275 K for 6 h under the CO ambience which was produced from the incomplete combustion of carbon at high-temperature.

After cooling down to room temperature (RT), the final products were ground into powders for subsequent analyses.

2.2. Characterizations. The phase purity of the synthetic samples was estimated by powder X-ray diffraction (P-XRD) on a Rigaku D-MAX 2200 VPC X-ray diffractometer of Cu K α ($\lambda = 1.5418 \text{ \AA}$) radiation at 40 kV and 26 mA. The P-XRD data for refinement were collected with the 2θ range from 5° to 110° and 2θ step of 0.02° on the Bruker D8 advanced X-ray diffractometer with a wavelength of 1.54056 \AA Cu K α radiation at 40 kV and 40 mA. The Rietveld refinement was performed using the TOPAS - Academic program.²²

The UV-vis excitation and emission spectra as well as the luminescence decay curves at room temperature (RT) were recorded on Edinburgh FLS 1000 Model spectrometer which was a combined fluorescence lifetime and steady-state, equipped with a cooled housing ($-20 \text{ }^\circ\text{C}$) photomultiplier PMT-900. The 450 W Xenon lamp was used as the excitation source of steady-state excitation and emission spectra. A 150 W nF900 lamp with a pulse width of 1 ns and pulse repetition rate of 40 kHz was used for the measurements of decay curves. The temperature-dependent spectral measurements in the 77-500 K range were performed by mounting the samples in an Oxford cryostat. The spectral measurements at 15 K were performed by mounting the samples in an Oxford cryostat with a closed cycle liquid helium apparatus and an Edinburgh FLS 920. The emission spectra of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ ($x = 0.001, 0.02, \text{ and } 0.06$) samples at 15 K as shown in Figure S1a,b,c were measured about a half of year later than that of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample in order to further confirm the dual-site occupancies of Eu^{2+} in RbBaPO_4 .

The excitation and emission spectra in the VUV-UV range were recorded on the 4B8 beam line of the Beijing Synchrotron Radiation Facility (BSRF). The sample was pressed into a pill with diameter of about 1 cm and thickness of about 0.2 cm for middle and far infrared reflectance (IR)

spectrum measurement on U4 beam line of National Synchrotron Radiation Laboratory (NSRL). For X-ray excited luminescence spectra measurements of 100 mg pressed pill samples at Delft University of Technology (The Netherlands), an X-ray tube with Tungsten anode operated at 80 kV was used as X-ray source.

3. RESULTS AND DISCUSSION

3.1. P-XRD Patterns and Structure




Figure 1. (a) The Rietveld refinement of P-XRD data of synthesized RbBaPO_4 sample; (b) the coordination environments of Ba^{2+} and Rb^+ sites; (c) the $2 \times 2 \times 2$ lattice cell structure of RbBaPO_4 .

Based on the P-XRD data of the synthesized RbBaPO₄ sample, Figure 1a shows the results of Rietveld refinement which is performed by using *Pnma* structure mode.^{20,23} The sample is of pure phase, and as-obtained reliability factors R_{wp} , R_p and R_B indicate well goodness of fitting results. The final refined structural parameters are listed in Table S1. The lattice constants a , b and c and unit cell volume V of RbBaPO₄ are 7.8178(8) Å, 5.7386(4) Å, 10.0586(0) Å, and 451.26(8) Å³, respectively.

RbBaPO₄ has two metal cation sites Ba²⁺ and Rb⁺. The coordination environments of Ba²⁺ and Rb⁺ sites are displayed in Figure 1b and the bond lengths of Ba²⁺-O²⁻ and Rb⁺-O²⁻ are listed in Table S2. Ba²⁺ ion is connected with nine O²⁻ ions with low point symmetry C_s , while Rb⁺ is larger than Ba²⁺ and coordinated by ten O²⁻ ligands. The average bond length of Ba²⁺-O²⁻ is ~2.855 Å, and that of Rb⁺-O²⁻ is ~3.031 Å. The nearest distance of Rb⁺-Rb⁺ (~4.177 Å) is close to that of Ba²⁺-Ba²⁺ (~4.064 Å). Figure 1c shows the 2×2×2 lattice cell structure of RbBaPO₄ host. The Rb⁺ ions mainly distribute along the b direction, while the Ba²⁺ ions parallelly distribute along the lattice plane of a and c axis to construct Ba²⁺ layers. The Ba²⁺ layers stack along the b crystal axis. The BaO₉, RbO₁₀ and PO₄ polyhedra form the RbBaPO₄ structure.

The P-XRD patterns of RbBa_{1-x}Eu_xPO₄ ($x = 0.001-0.08$) samples and the refined result of RbBaPO₄ are shown in Figure S2. All samples are in agreement with the refined results. This indicates that Eu²⁺ ions are successfully incorporated into RbBaPO₄ lattices. The high-quality P-XRD patterns of selected RbBa_{1-x}Eu_xPO₄ ($x = 0.02, 0.04$ and 0.08) samples and their Rietveld refinement results are shown in Figure S3a,b,c. The obtained reliability factors R_{wp} , R_p and R_B indicate a good refined quality. It is demonstrated that RbBa_{1-x}Eu_xPO₄ samples are single purity phase.

3.2. VUV-UV-vis Photoluminescence of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$




Figure 2. (a) The synchrotron radiation VUV-UV excitation ($\lambda_{\text{em}} = 407 \text{ nm}$; 10 K) and the highest-height normalized lab UV-vis excitation ($\lambda_{\text{em}} = 406$ and 440 nm ; 15 K) spectra of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample; (b) the highest-height normalized emission ($\lambda_{\text{ex}} = 325, 360$ and 390 nm ; 15 K) spectra of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample; (c) the decay curves ($\lambda_{\text{ex}} = 310 \text{ nm}, \lambda_{\text{em}} = 408$ and $\lambda_{\text{ex}} = 360 \text{ nm}, \lambda_{\text{em}} = 435 \text{ nm}$; 77 K) of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample.

The plots (a) and (b) of Figure 2 are the VUV-UV excitation spectrum ($\lambda_{\text{em}} = 407 \text{ nm}$) recorded with synchrotron radiation facility at BSRF at 10 K, the highest-height normalized UV-vis excitation ($\lambda_{\text{em}} = 406$ and 440 nm) and the emission ($\lambda_{\text{ex}} = 325, 360$ and 390 nm) spectra collected

by FLS 920 spectrometer of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample at 15 K. It shows that the excitation intensity below ~ 200 nm in Figure 2a is very weak. For host compounds with similar compositions to RbBaPO_4 , we found in previous work the host exciton peaks at ~ 7.61 eV in NaCaPO_4 and ~ 7.65 eV in KSrPO_4 , respectively.^{17,20} The weak excitonic absorption in the current case may relate to the low energy transfer probability from host to doping Eu^{2+} ions, the delocalization of Eu^{2+} 5d-electron into the conduction band when the high-lying 5d excited states are higher than the conduction band minimum,²⁴ and/or other unknown reasons. To determine the exciton peak location of RbBaPO_4 , the VUV excitation spectra of two samples $\text{Rb}_{1.02}\text{Ba}_{0.96}\text{Gd}_{0.02}\text{PO}_4$ and $\text{Rb}_{1.003}\text{Ba}_{0.994}\text{Ce}_{0.003}\text{PO}_4$ were recorded at 10 K and shown in Figure S4 and Figure S5, respectively. The host exciton peak (E_{ex}) is found to be ~ 7.37 eV (168 nm) in Figure S4 and ~ 7.43 eV (167 nm) in Figure S5. The mean value 7.40 ± 0.03 eV of RbBaPO_4 found from Figure S4 and Figure S5 is compatible with the values of NaCaPO_4 and KSrPO_4 .^{17,20} So the band gap of RbBaPO_4 is estimated to be 7.84 eV after extra adding exciton binding energy ($0.008 \times E_{\text{ex}}^2 = 0.44$ eV) to E_{ex} (7.40 eV).

The strong excitation bands beyond 220 nm result from 4f-5d transitions of Eu^{2+} . The profiles of the two excitation curves in the 300-410 nm range are somewhat different, by monitoring emissions at 406 and 440 nm, respectively. The excitation band of 440 nm emission slightly shifts to the long-wavelength side in comparison with that of 406 nm emission. We suspect that these observations relate to different site occupancies of Eu^{2+} in $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample and will discuss this issue below.

Upon 325 nm excitation, we record the main emission peak at about 406 nm and a weak shoulder band at about 431 nm in Figure 2b. When we move the excitation wavelength to 360 nm and 390 nm, the shoulder emission band gradually becomes more pronounced and the main emission peak slightly shifts to about 407 and 410 nm. The phenomenon can be seen not only in this

RbBa_{0.995}Eu_{0.005}PO₄ sample, but also in other samples. As shown in Figure S1a,b,c, similar results were recorded in samples RbBa_{1-x}Eu_xPO₄ (x = 0.001, 0.02 and 0.06) although these three samples were stored for about half a year before the measurement. The main peak shifts to the long-wavelength direction and the shoulder band is more conspicuous under 390 nm excitation in comparison with that under 325 and 360 nm excitation. These observations are somewhat different from that in references, in which only a broad asymmetric band was seen, but no shoulder band was found in the emission spectra.^{16,19} Besides, the emission peaks were reported to shift to longer wavelengths with the increase of Eu²⁺ concentrations, and the red-shift of emission band was explained by the change in the crystal field around Eu²⁺. Because no impurity phase was detected in these samples as mentioned in section 3.1, we think that the dual-site occupancies of Eu²⁺ ions may be the main reason for the evolution of the emission profile under different excitation wavelengths in this paper. Since Ba²⁺ and Eu²⁺ ions have similar ionic radii and the same valence states, the Ba²⁺ site should be one of the two sites that Eu²⁺ occupies.

The emission energy of Eu²⁺ at the Ba²⁺ site of RbBaPO₄ can be predicted using equation: $E(\text{Eu}^{2+}) = (0.64 \pm 0.02) \times E(\text{Ce}^{3+}) + (0.53 \pm 0.06) \text{ eV}$.²⁵ Ce³⁺ ions have been reported to occupy Ba²⁺ sites in RbBaPO₄.¹⁸ In Figure S5, the doublet 5d₁-²F_{5/2,7/2} emissions of Ce³⁺ in Rb_{1.003}Ba_{0.994}Ce_{0.003}PO₄ are approximately observed at 3.83 and 3.58 eV, respectively. Using above equation, the emission energy of Eu²⁺ at the Ba²⁺ site of RbBaPO₄ is predicted to be at $2.98 \pm 0.14 \text{ eV}$ (~416 nm). This position is closer to the main peak at about 406 nm and shows more different from the shoulder band at about 431 nm. It seems to imply that the main peak at 406 nm is from the emission of Eu²⁺ at the Ba²⁺ site, and the shoulder band the emission of Eu²⁺ at another type of site. However, due to the error margin of approximately 0.2 eV of the prediction, we do not merely use this prediction as an unambiguous argument to assign the site occupancies of Eu²⁺ ions.

The site nature can be further understood by the comparison of the emission of Eu^{2+} in isomorphous host compounds KSrPO_4 , KBaPO_4 and RbBaPO_4 .^{20,26,27} These compounds crystallize in an orthorhombic structure with the space group $Pnma$, and have a single nine-fold coordinated Sr^{2+} or Ba^{2+} site with C_s point symmetry. Referring to the data in Table S3, the emission peak of Eu^{2+} at Ba^{2+} site of KBaPO_4 has been observed at 419 ± 2 nm, and that at Sr^{2+} site of KSrPO_4 was found at 423 ± 1 nm.^{19,20,26} Since the BaO_9 polyhedron is larger than that of SrO_9 , the crystal field splitting (CFS) energy of Eu^{2+} 5d orbital at the Ba^{2+} site is likely to be smaller than that at the Sr^{2+} site. As a result, the emission wavelength of Eu^{2+} at the Ba^{2+} site of KBaPO_4 (419 ± 2 nm) is expected at slightly shorter wavelength than that at the Sr^{2+} site of KSrPO_4 (423 ± 1 nm). Similarly, it is expected that the emission peak of Eu^{2+} at the Ba^{2+} site of isomorphous $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ locates at shorter wavelength ($< 423 \pm 1$ nm). So the main peak of about 406 nm is attributed to the emission of Eu^{2+} at Ba^{2+} site of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ [marked as $\text{Eu}^{2+}(\text{I})$], and the shoulder band of about 440 nm is ascribed to the emission of Eu^{2+} at another type of site [labelled as $\text{Eu}^{2+}(\text{II})$]. The $\text{Eu}^{2+}(\text{II})$ is most likely Eu^{2+} in Rb^+ site in consideration of the structure of RbBaPO_4 .

To evaluate the positions of main and shoulder bands, the emission curves were fitted with a sum of two Gaussian functions (Figure S6). Under 325 nm excitation, two peaks are at $\sim 24.6 \times 10^3$ cm^{-1} (406 nm) and $\sim 23.2 \times 10^3$ cm^{-1} (431 nm). They show a slight redshift when excited at 360 nm. Upon 390 nm excitation, the two peaks shift to $\sim 24.4 \times 10^3$ cm^{-1} (410 nm) and $\sim 23.1 \times 10^3$ cm^{-1} (433 nm). The longer wavelength is more likely to excite $\text{Eu}^{2+}(\text{II})$ ions, so the relative intensity of $\text{Eu}^{2+}(\text{II})$ emission becomes gradually stronger under 325, 360 and 390 nm excitation. Two factors, the increasing emission intensity of $\text{Eu}^{2+}(\text{II})$ and the conjoint influences of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ emissions, make both bands look like to shift towards longer wavelengths in fitting results. The

increase of $\text{Eu}^{2+}(\text{II})$ emission draws the main emission peak towards the long wavelength direction, and the redshift of main peak, in turn, makes the shoulder band appear at longer wavelength side.

Finally, we recorded two decay curves ($\lambda_{\text{ex}} = 310 \text{ nm}$, $\lambda_{\text{em}} = 408$; $\lambda_{\text{ex}} = 360 \text{ nm}$, $\lambda_{\text{em}} = 435 \text{ nm}$) of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ in $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ at 77 K that are displayed in Figure 2c. Decay curves show an exponential characteristic. Each decay curve was fitted with single exponential decay functions to obtain the lifetimes $\tau_1 = 383 \text{ ns}$ and $\tau_2 = 460 \text{ ns}$ for $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$, respectively. They are in the range of lifetimes reported for other Eu^{2+} doped materials with similar emission wavelength, such as $\text{BaMgSiO}_4: 0.007 \text{ Eu}^{2+}$ (420 nm, $\sim 324 \text{ ns}$),²⁸ $\text{SrAl}_3\text{BO}_7: 0.03 \text{ Eu}^{2+}$ (410 nm, $\sim 430 \text{ ns}$),²⁹ and $\text{K}_{0.2}\text{Rb}_{0.8}\text{BaPO}_4: 0.03 \text{ Eu}^{2+}$ (424 nm, $\sim 484 \text{ ns}$).¹⁹ The ratio τ_1/τ_2 (~ 0.83) is close to the ratio $\frac{\lambda_1^3}{\lambda_2^3}$ ($= \frac{406^3}{431^3} = 0.84$), because radiative decay time is proportional to the third power of the average emission wavelength in a given host.³⁰

3.3. Electron-Vibrational Interaction and Temperature-Dependent Luminescence of Eu^{2+} in $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$




Figure 3. (a) The experimental and fitted synchrotron radiation infrared reflectance spectrum of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ at RT; (b) the emission spectrum ($\lambda_{\text{ex}} = 360 \text{ nm}$; 15 K) and corresponding electron-vibrational interaction (EVI) analysis.

The Eu^{2+} emission band is formed by a series of electron-vibrational transition lines that have been broadened and smoothed by lattice dispersion. The band shape of Eu^{2+} can be described by the Pekarian-type spectral distribution which can be simplified to eqs. (1, 2) at low temperature ($kT \leq \hbar\omega$).³¹ Because the doping content is low ($x = 0.005$) in the case of Figure 3, we neglect the interactions of 5d excited state and 4f ground state between $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ systems herein, and roughly regard the total Eu^{2+} emission shape as the sum of the two independent $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ emission shapes as expressed in eq. (3).

$$I = \frac{e^{-S} \cdot S^P}{P!} \left(1 + S^2 \cdot \frac{e^{-\hbar\omega/kT}}{P+1} \right) \quad (1)$$

$$P = \frac{E_0 - E}{\hbar\omega} \quad (2)$$

$$I_{\text{total}} = A_1 \cdot \frac{e^{-S_1} \cdot S_1^{P_1}}{P_1!} \left(1 + S_1^2 \cdot \frac{e^{-\frac{\hbar\omega_1}{kT}}}{P_1+1} \right) + A_2 \cdot \frac{e^{-S_2} \cdot S_2^{P_2}}{P_2!} \left(1 + S_2^2 \cdot \frac{e^{-\frac{\hbar\omega_2}{kT}}}{P_2+1} \right) \quad (3)$$

Where A_1 and A_2 are the emission ratios of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$, S_1 and S_2 are the Huang-Rhys factors, $\hbar\omega_1$ and $\hbar\omega_2$ the effective phonon energies, and P_1 and P_2 are the number of effective phonons coupled with $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ emissions; k is the Boltzmann constant [$6.950 \times 10^{-1} \text{ (cm K)}^{-1}$] and T is temperature (15 K).

To estimate the possible effective phonon energies, the middle-far IR spectrum of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ in wavenumber 50-1500 cm^{-1} range was measured at RT using synchrotron radiation facility at NSRL as shown in Figure 3a. The experimental curve is fitted with a model for the complex dielectric function consisting of Lorentz oscillators.

$$\varepsilon(\omega) = \varepsilon_{\infty} + \sum_k \frac{\omega_{p,k}^2}{\omega_{0,k}^2 - \omega^2 - k\gamma_k\omega} \quad (4)$$

Where ε_{∞} is the real part of the complex dielectric function at high frequency; $\omega_{p,k}$, $\omega_{0,k}$ and γ_k are the plasma frequency, phonon frequency and damping factor of the k-th oscillator, respectively. The fitting curve is shown in Figure 3a and fitting parameters are listed in Table S4, which provide the initial referred $\hbar\omega_1$ and $\hbar\omega_2$ values for the following fitting procedure of electron-vibrational interaction (EVI) analysis of Eu^{2+} emissions in $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$.

We select the emission spectrum under 360 nm excitation for the EVI analysis and show the fitting results in Figure 3b. The simulated parameters of EVI analysis of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample are listed in Table 1. The coincidence of fitted and experimental curves indicates a good simulation quality. The fitted emission peaks of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ are approximately located at 24.4×10^3 and $22.8 \times 10^3 \text{ cm}^{-1}$, which are near the Gaussian fitting results ($\sim 24.6 \times 10^3$ and $\sim 23.2 \times 10^3 \text{ cm}^{-1}$, respectively). As a result, the energies of zero-phonon lines (ZPLs) of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ are estimated to be $25.8 \times 10^3 \text{ cm}^{-1}$ (388 nm) and $24.7 \times 10^3 \text{ cm}^{-1}$ (405 nm), respectively. The ZPL energy of $\text{Eu}^{2+}(\text{I})$ is close to the location of the intersection ($25.6 \times 10^3 \text{ cm}^{-1}$, 390 nm) between the normalized excitation spectrum of 406 nm emission and normalized emission spectrum at 325 nm excitation.¹³ The effective phonon energies of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ are estimated to be 204 and 221 cm^{-1} , which are close to the value 207.28 cm^{-1} in Table S4. Hence the Stokes shift values ΔS for $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ are calculated to be 2.62×10^3 and $3.60 \times 10^3 \text{ cm}^{-1}$ according to $\Delta S = (2S-1) \cdot \hbar\omega$, respectively.

Table 1. The Simulated Parameters via EVI Analysis in RbBa_{0.995}Eu_{0.005}PO₄ Sample.

Parameters	Values
A_1	1.74×10^7
S_1	6.91
$\hbar\omega_1$ (cm ⁻¹)	204
$E_0(1)$ (cm ⁻¹)	25.8×10^3
A_2	6.95×10^6
S_2	8.64
$\hbar\omega_2$ (cm ⁻¹)	221
$E_0(2)$ (cm ⁻¹)	24.7×10^3




Figure 4. (a) The temperature-dependent emission map ($\lambda_{\text{ex}} = 310$ nm) of RbBa_{0.995}Eu_{0.005}PO₄ sample; (b) the normalized emission spectra ($\lambda_{\text{ex}} = 310$ nm) of RbBa_{0.995}Eu_{0.005}PO₄ sample at 77 and 500 K, and corresponding Gaussian fitting results of emission spectra.

The temperature-dependent emission map ($\lambda_{\text{ex}} = 310 \text{ nm}$) of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample is shown in Figure 4a. With increasing temperature, the intensity of Eu^{2+} emission decreases gradually. To analyze the influence of temperature on emission shape of Eu^{2+} in the two sites, the emission spectra of 77 and 500 K are selected to be normalized and shown in Figure 4b. With raising temperature, the emission band broadens to the larger wavenumber side. The observation may relate to the different thermal-quenching and different thermal-broadening characteristics of two luminescent centers. As a rough estimation, each emission spectrum is fitted by a sum of two Gaussian functions. When temperature increases from 77 to 500 K, the integrated intensity of $\text{Eu}^{2+}(\text{I})$ decreases about 35% and that of $\text{Eu}^{2+}(\text{II})$ about 44%, but the value of the full width at half maximum (FWHM) of $\text{Eu}^{2+}(\text{I})$ increases approximately 58% (from $\sim 1.35 \times 10^3$ to $\sim 2.1 \times 10^3 \text{ cm}^{-1}$) and that of $\text{Eu}^{2+}(\text{II})$ approximately 47% (from $\sim 1.83 \times 10^3$ to $\sim 2.69 \times 10^3 \text{ cm}^{-1}$).

3.4. Concentration-Dependent Luminescence Spectra and Energy Transfer Dynamics of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ samples




Figure 5. (a) The normalized emission ($\lambda_{\text{ex}} = 310 \text{ nm}$) spectra of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ ($x = 0.001-0.08$) samples at RT; (b) the dependencies of total integral area in 380-490 nm range (curve A), main

peak height (curve B) and the height at 431 nm (curve C) on doping concentrations (x values) in $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$.

To investigate the effect of concentration on $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ emission, we collected the emission spectra of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ with different doping concentrations ($x = 0.001-0.08$) under 310 nm excitation at RT. Figure 5a shows normalized emission spectra of these samples in terms of the integral intensity of the emission bands. The shoulder band at long wavelength hand lifts gradually with increasing concentration. Meantime, the main emission peak shifts gradually from 406 to 415 nm. These tendencies become more obvious when the doping concentration (x) is above 0.04. According to emission spectra of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ in Figure S7, we estimated the total integral area in 380-490 nm range, read the main peak height and the height at 431 nm, and plotted them as a function of doping concentration (x value) in Figure 5b. Herein, the main peak height and the height at 431 nm are regarded as rough indicators of emission intensities of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$, respectively. The main peak height increases at first, and reaches a maximum when $x = 0.03$, then decreases with increasing doping concentrations. In contrast, the height at 431 nm always increase with increasing x value except for the point of $x = 0.04$. As a whole, the integral intensity of Eu^{2+} clearly increases with increasing content until $x = 0.03$, and then keeps almost invariable except for the deviation point with $x = 0.04$. The observations may relate to the factors such as site occupancies, energy transfer between $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$, and crystal field splitting at different doping levels in following discussions.

At first, when the doping concentration is very low ($x = 0.001$), Eu^{2+} mainly occupies the Ba^{2+} site and $\text{Eu}^{2+}(\text{I})$ emission is dominant. $\text{Eu}^{2+}(\text{I})$ emission intensity regularly increases until $x = 0.03$ due to the increase of population of Eu^{2+} in Ba^{2+} sites. Then the increase of energy transfer rates

of $\text{Eu}^{2+}(\text{I}) \rightarrow \text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{I}) \rightarrow \text{Eu}^{2+}(\text{II})$ results in the quenching of $\text{Eu}^{2+}(\text{I})$ emission when $x > 0.03$, and the main peak height decreases. The intensity of $\text{Eu}^{2+}(\text{II})$ emission gradually increases, which is ascribed to the contribution of energy transfer from $\text{Eu}^{2+}(\text{I})$ to $\text{Eu}^{2+}(\text{II})$ and the increase of $\text{Eu}^{2+}(\text{II})$ population with the increase of doping concentration.

For the redshift of whole emission band, the crystal field effect on Eu^{2+} in RbBaPO_4 has been regarded as the main reason.^{16,19} This can be interpreted because the ionic radii increase with the relative order $\text{Eu}^{2+} < \text{Ba}^{2+} < \text{Rb}^+$ in case of nine- or ten-fold coordination surroundings.³² With the increase of doping concentration, the $\text{Eu}^{2+}\text{-O}^{2-}$ bond distance is expected to be somewhat shorten, and the 5d electron of Eu^{2+} experiences a larger crystal field strength. The possible changes in the crystal field around Eu^{2+} are responsible for this shift as reported in $\text{BaMg}_2\text{Si}_2\text{O}_7$, $\text{Ba}(\text{PO}_3)_2$, $\text{K}_2\text{BaCa}(\text{PO}_4)_2$ and so on.^{15,33,34} When we assume that the energies of the 5d centroid and the Stokes shift are relatively invariant, the 5d-4f emissions of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ shift to long wavelength side due to the increase of 5d crystal field splitting of $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$, respectively. Besides, the increase of the $\text{Eu}^{2+}(\text{II})$ component and the decrease of $\text{Eu}^{2+}(\text{I})$ also provide a contribution to this redshift.

Further, the energy transfer dynamics is studied on the basis of decay curves. Figure 6a shows the decay curves ($\lambda_{\text{ex}} = 310 \text{ nm}$, $\lambda_{\text{em}} = 407 \text{ nm}$) of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ ($x = 0.001\text{-}0.08$) samples at RT. At low doping contents with $x = 0.001$ and 0.003 , the decay curves are close to single exponential. When x increases, the decay curves deviate gradually from that of the low doping cases. Several mechanisms of energy transfer such as multipolar and even exchange interactions could make contributions to the deviation. Since the exchange interaction only occurs in very short distances ($\sim 5 \text{ \AA}$), the multipolar interactions are expected to be dominated for our samples with the doping content below 10%. To estimate the type of multipolar interaction of energy transfer, we only

consider the energy transfer from $\text{Eu}^{2+}(\text{I})$ to $\text{Eu}^{2+}(\text{II})$ without energy migration between donor $\text{Eu}^{2+}(\text{I})$ ions firstly and simulate the decay curves of donor $\text{Eu}^{2+}(\text{I})$ with the Inokuti-Hirayama model as follows:³⁵

$$I(t) = I(0) \exp\left[-\frac{t}{\tau_0} + Q \cdot (t)^{\frac{3}{s}}\right] \quad (5)$$

$$Q = -\frac{4\pi}{3} n_a \Gamma\left(1 - \frac{3}{s}\right) \cdot (C_{\text{DA}}^{(s)})^{3/s} \quad (6)$$

$$\ln\left(-\ln\left(\frac{I(t)}{I(0)}\right) - \frac{t}{\tau_0}\right) = \ln(-Q) + \frac{3}{s} \ln(t) \quad (7)$$

Where $I(t)$ is emission intensity of Eu^{2+} at time t and $I(0)$ is the emission intensity at $t = 0$; n_a is the concentration (m^{-3}) of $\text{Eu}^{2+}(\text{II})$ at Rb^+ site, its initial value is estimated by the doping concentration (0.04 or 0.08) before the simulation procedure; $C_{\text{DA}}^{(s)}$ is energy transfer microparameter, which has a relation of energy transfer probability. $\Gamma(1-3/s)$ is the gamma function and s parameter depends on the type of electric-multipolar interaction. The s values are 6, 8, and 10 for the dipole-dipole, dipole-quadrupole, and quadrupole-quadrupole interactions, respectively. We mathematically make a transformation and plot the $\ln(-\ln(I(t)/I(0))-t/\tau_0)$ as a function of $\ln(t)$ as shown in the inset of Figure 6a. The s value is obtained by the slope $3/s$ from a linear fitting to decay curves with eq. (7). The average s value 6.2 is close to 6, implying that the dominant mechanism of Eu^{2+} in RbBaPO_4 compound is the dipole-dipole interaction. The result is consistent with the knowledge that Eu^{2+} involves Laporte allowed transitions, and the non-radiative energy transfer between $\text{Eu}^{2+}(\text{I})$ and $\text{Eu}^{2+}(\text{II})$ would be mainly dipole-dipole mechanism. It is also in agreement with the reported result on the basis of emission spectra.¹⁶ The decay curves are simulated with eq. (5). The fitting quality R_{adj}^2 is all more than 0.99. Table S5 lists other fitting parameters of simulation via this model.




Figure 6. (a) The decay curves ($\lambda_{ex} = 310$ nm, $\lambda_{em} = 407$ nm) of $RbBa_{1-x}Eu_xPO_4$ ($x = 0.001-0.08$) samples at RT and fitting curves via Inokuti-Hirayama model [eq. (5)], the inset shows linear fitting results with eq. (7); (b) the decay curves ($\lambda_{ex} = 310$ nm, $\lambda_{em} = 407$ nm) of $RbBa_{1-x}Eu_xPO_4$ ($x = 0.04$ and 0.08) samples at RT and fitting curves via Yokota-Tanimoto model [eqs. (8, 9)].

In addition, the simulation with the slow energy diffusion model of Yokota-Tanimoto [eqs. (8, 9)] is applied to verify the energy transfer from $Eu^{2+}(I)$ to $Eu^{2+}(II)$ and possible energy migration between $Eu^{2+}(I)$.^{36,37}

$$I(t) = I(0) \exp\left(\frac{-t}{\tau_0}\right) \exp\left(Q \cdot t^{3/s} \left(\frac{1+10.87x+15.50x^2}{1+8.743x}\right)^{3/4}\right) \quad (8)$$

$$x = D \cdot C_{DA}^{-1/3} \cdot t^{2/3} \quad (9)$$

$$D = 0.5(4\pi n_d/3)^{4/3} \cdot C_{DD} \quad (10)$$

Where $I(t)$ is emission intensity of Eu^{2+} at time t , and $I(0)$ is the emission intensity when $t = 0$; n_a is acceptors concentration (m^{-3}), which is the concentration of $Eu^{2+}(II)$ in our case and n_d is concentration (m^{-3}) of donors $Eu^{2+}(I)$, their initial values are estimated by the doping concentration (0.04 or 0.08) and emission ratio of $Eu^{2+}(I)$ to $Eu^{2+}(II)$ as mentioned in Section 3.3; C_{DA} is energy transfer microparameter; Q is also expressed as eq. (6); C_{DD} is energy migration microparameter; x contains the variable t and is expressed in eq. (9); D is diffusion parameter; τ_0 is the lifetime of

$\text{Eu}^{2+}(\text{I})$ in the situation of no $\text{Eu}^{2+}(\text{II})$ acceptors around, and set to be $\tau_{\text{av}} = 440$ ns from the decay curves of $x = 0.001$ and 0.003 . This model is valid in the limit of weak diffusion between donors ($C_{\text{DD}} \ll C_{\text{DA}}$). When s parameter is close to 6, the best agreement of fitted curves with experimental data has been achieved as shown in Figure 6b. It indicates that the mechanism of energy transfer is mainly dipole-dipole interaction. The fitting parameters are summarized in Table S5. The average C_{DA} parameter is about $2.52 \times 10^{-48} \text{ m} \cdot \text{s}^{-1}$, and average C_{DD} parameter is about $1.99 \times 10^{-50} \text{ m} \cdot \text{s}^{-1}$, which satisfies the using rule of Yokota-Tanimoto model. Because the diffusion parameter D is not zero and becomes larger at higher doping content, energy migration between $\text{Eu}^{2+}(\text{I})$ also takes part in the process of $\text{Eu}^{2+}(\text{I}) \rightarrow \text{Eu}^{2+}(\text{II})$ energy transfer. But the energy migration between $\text{Eu}^{2+}(\text{I})$ is weak in comparison with $\text{Eu}^{2+}(\text{I}) \rightarrow \text{Eu}^{2+}(\text{II})$ energy transfer. Therefore, the decay of $\text{Eu}^{2+}(\text{I})$ is mainly caused by energy transfer from $\text{Eu}^{2+}(\text{I})$ to $\text{Eu}^{2+}(\text{II})$ with the mechanism of dominant dipole-dipole interaction. When energy transfer probability shows the same rate as the decay rate ($1/\tau_0$) of isolated $\text{Eu}^{2+}(\text{I})$, the critical distance R_c is calculated to be about 11 \AA .

3.5. X-ray Radioluminescence of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$




Figure 7. The X-ray excited emission spectra of RbBa_{0.995}Eu_{0.005}PO₄ sample and crystal BaF₂ at RT.

Figure 7 shows emission spectra of RbBa_{0.995}Eu_{0.005}PO₄ sample and crystal BaF₂ under excitation of X-ray at RT. The crystal BaF₂ is measured as a reference, and its absolute scintillation light yields is measured to be ~10000 ph/MeV (photons emitted per MeV absorbed X-ray energy). The emission band maxima at 226 and 310 nm originate from the core valence luminescence and self-trapped-exciton emission.³⁸ The asymmetric emission band in the RbBa_{0.995}Eu_{0.005}PO₄ sample is from Eu²⁺(I) and Eu²⁺(II) emissions. The X-ray excited emission spectrum of RbBa_{0.995}Eu_{0.005}PO₄ sample is in line with that under VUV-UV excitation. Based on the calculated ratio of integrated intensity to that of BaF₂, the estimated light yield (η) for RbBa_{0.995}Eu_{0.005}PO₄ is 17700 ± 1800 ph/MeV, showing its potential application in X-ray detecting.

4. CONCLUSIONS

In summary, we have prepared the compound RbBaPO_4 doped with different concentrations of Eu^{2+} ions, the Rietveld refinement of P-XRD data confirms that two types of polyhedrons for metal ions occur in the host compound. The RbO_{10} and BaO_9 polyhedrons are with same C_s point symmetry. By using the structural data and the semi-empirical formulas, we assign the doublet emission bands of Eu^{2+} ions with the maxima at ~ 406 and ~ 431 nm to arising from Eu^{2+} in Ba^{2+} and Rb^+ sites, respectively. The EVI analysis and the temperature-dependent luminescence further corroborate this assignment. Besides, the Huang-Rhys factors, the ZPLs and the Stokes shifts of Eu^{2+} in Ba^{2+} and Rb^+ sites are estimated by EVI analysis. The energy transfer dynamics are studied by the measurements on the emission decays of donor Eu^{2+} in Ba^{2+} site, and simulated with Inokuti-Hirayama model and Yokota-Tanimoto model. The results show that the dominant mechanism of energy transfer is electric dipole-dipole interaction. The light yield value 17700 ± 1800 ph/MeV of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ estimated from the X-ray excited spectrum indicates the possible application of this phosphor in X-ray detecting after further optimization.

ASSOCIATED CONTENT

Supporting Information

P-XRD patterns and Rietveld refinement of P-XRD data of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ samples, Refined structural parameters of RbBaPO_4 sample, Fitting parameters for the Synchrotron radiation middle-far IR spectrum of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ via the complex dielectric function, Fitting parameters of energy transfer dynamics via two models, Highest-height normalized emission spectra (15 K) of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ under different excitation wavelengths, VUV-UV excitation and emission spectra (10 K) of $\text{Rb}_{1.02}\text{Ba}_{0.96}\text{Gd}_{0.02}\text{PO}_4$ and $\text{Rb}_{1.003}\text{Ba}_{0.994}\text{Ce}_{0.003}\text{PO}_4$ samples, Highest-height normalized emission spectra of $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ sample and corresponding Gaussian fitting results, Emission spectra of $\text{RbBa}_{1-x}\text{Eu}_x\text{PO}_4$ samples.

AUTHOR INFORMATION

Corresponding Author

Hongbin Liang – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China;

Email: cesbin@mail.sysu.edu.cn

Authors

Rongfu Zhou – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

Fengkai Ma – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

Fang Su – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

Yiyi Ou – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

Zeming Qi – National Synchrotron Radiation Laboratory, University of Science and Technology of China, Hefei 230029, P. R. China

Jianhui Zhang – MOE Key Laboratory of Bioinorganic and Synthetic Chemistry, KLGHEI of Environment and Energy Chemistry, School of Chemistry, Sun Yat-sen University, Guangzhou 510275, P. R. China

Yan Huang – Beijing Synchrotron Radiation Facility, Institute of High Energy Physics, Chinese Academy of Sciences, Beijing 100039, P. R. China

Pieter Dorenbos – *Faculty of Applied Sciences, Delft University of Technology, Mekelweg 15, 2629 JB Delft, The Netherlands*

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

This work is financially supported by the National Natural Science Foundation of China (21671201 and 61905289).

REFERENCES

- (1) Blasse, G.; Grabmaier, B. C. *Luminescent Materials*. Springer. Verlag Berlin Heidelberg. **1994**.
- (2) Matsuzawa, T.; Aoki, Y.; Takeuchi, N.; Murayama, Y. A New Long Phosphorescent Phosphor with High Brightness, SrAl₂O₄: Eu²⁺, Dy³⁺. *J. Electrochem. Soc.* **1996**, *143*, 2670.
- (3) Dorenbos, P. Fundamental Limitations in the Performance of Ce³⁺-, Pr³⁺-, and Eu²⁺- Activated Scintillators. *IEEE Trans. Nucl. Sci.* **2010**, *57*, 1162-1167.
- (4) Pust, P.; Weiler, V.; Hecht, C.; Tücks, A.; Wochnik, A. S.; Henß, A. K; Wiechert, D.; Scheu, C.; Schmidt, P. J.; Schnick, W. Narrow-Band Red-Emitting Sr[LiAl₃N₄]: Eu²⁺ as a Next-Generation LED-Phosphor Material. *Nat. Mater.* **2014**, *13*, 891-896.
- (5) Tang, Z.; Zhang, G.; Wang, Y. Design and Development of a Bluish-Green Luminescent Material (K₂HfSi₃O₉: Eu²⁺) with Robust Thermal Stability for White Light-Emitting Diodes. *ACS Photonics* **2018**, *5*, 3801-3813.

(6) Ma, F.; Su, F.; Zhou, R.; Ou, Y.; Xie, L.; Liu, C.; Jiang, D.; Zhang, Z.; Wu, Q.; Su, L.; Liang, H. The Defect Aggregation of RE³⁺ (RE=Y, La ~ Lu) in MF₂ (M=Ca, Sr, Ba) Fluorites. *Mater. Res. Bull.* **2020**, *125*, 110788.

(7) Shi, R.; Lin, L.; Huang, Y.; Tao, Y.; Zheng, L.; Li, Z.; Liang, H. Li₄SrCa(SiO₄)₂: Eu²⁺: A Potential Temperature Sensor with Unique Optical Thermometric Properties. *ACS Appl. Mater. Interfaces* **2019**, *11*, 9691-9695.

(8) Dutta, S.; Som, S.; Meena, M. L.; Chaurasiya, R.; Chen, T. M. Multisite-Occupancy-Driven Intense Narrow-Band Blue Emission from Sr₅SiO₄Cl₆: Eu²⁺ Phosphor with Excellent Stability and Color Performance. *Inorg. Chem.* **2020**, *59*, 1928-1939.

(9) Liao, H.; Zhao, M.; Molokeev, S. M.; Liu, Q.; Xia, Z. Learning from a Mineral Structure toward an Ultra-Narrow-Band Blue-Emitting Silicate Phosphor RbNa₃(Li₃SiO₄)₄: Eu²⁺. *Angew. Chem. Int. Ed.* **2018**, *57*, 11728-11731.

(10) Qiao, J.; Zhou, G.; Zhou, Y.; Zhang, Q.; Xia, Z. Divalent Europium-Doped Near-Infrared-Emitting Phosphor for Light-Emitting Diodes. *Nat. Commun.* **2019**, *10*, 5267.

(11) Hou, D.; Ma, C. G.; Liang, H.; Brik, M. G. Electron-Vibrational Interaction in the 5d States of Eu²⁺ Ions in Sr_{6-x}Eu_xBP₅O₂₀ (x = 0.01-0.15). *ECS J. Solid State Sci. Technol.* **2014**, *3*, R39-R42.

(12) Nazarov, M.; Brik, M.G.; Spassky, D.; Tsukerblat, B. Crystal Field Splitting of 5d States and Luminescence Mechanism in SrAl₂O₄: Eu²⁺ Phosphor. *J. Lumin.* **2017**, *182*, 79-86.

(13) Ou, Y.; Zhou, W.; Hou, D.; Brik, M. G.; Dorenbos, P.; Huang, Y.; Liang, H. Impacts of 5d Electron Binding Energy and Electron-Phonon Coupling on Luminescence of Ce³⁺ in Li₆Y(BO₃)₃. *RSC Adv.* **2019**, *9*, 7908-7915.

(14) Zhang, L.; Zhang, J.; Pan, G.; Zhang, X.; Hao, Z.; Luo, Y.; Wu, H. Low-Concentration Eu²⁺-Doped SrAlSi₄N₇: Ce³⁺ Yellow Phosphor for wLEDs with Improved Color-Rendering Index. *Inorg. Chem.* **2016**, *55*, 9736-9741.

(15) Ou, Y.; Zhou, W.; Liu, C.; Lin, L.; Brik, M. G.; Dorenbos, P.; Tao, Y.; Liang, H. Vacuum Referred Binding Energy Scheme, Electron–Vibrational Interaction, and Energy Transfer Dynamics in BaMg₂Si₂O₇: Ln (Ce³⁺, Eu²⁺) Phosphors. *J. Phys. Chem. C* **2018**, *122*, 2959-2967.

(16) Song, H.; Yim, D.; Roh, H.; Cho, I.; Kim, S.; Jin, Y.; Shim, H.; Kim, D.; Hong, K. RbBaPO₄: Eu²⁺: A New Alternative Blue-Emitting Phosphor for UV-Based White Light-Emitting Diodes. *J. Mater. Chem. C* **2013**, *1*, 500-505.

(17) Wang, Y.; Brik, M. G.; Dorenbos, P.; Huang, Y.; Tao, Y.; Liang, H. Enhanced Green Emission of Eu²⁺ by Energy Transfer from the ⁵D₃ Level of Tb³⁺ in NaCaPO₄. *J. Phys. Chem. C* **2014**, *118*, 7002-7009.

(18) Chen, J.; Zhao, W.; Zhong, J.; Lan, L.; Wang, J.; Wang, N. Synthesis and Luminescence Properties of Ce³⁺-Doped RbBaPO₄. *Ceram. Int.* **2014**, *40*, 15241-15248.

(19) Zhao, C.; Xia, Z.; Yu, S. Thermally Stable Luminescence and Structure Evolution of (K, Rb)BaPO₄: Eu²⁺ Solid-Solution Phosphors. *J. Mater. Chem. C* **2014**, *2*, 6032-6039.

(20) Zhou, R.; Lin, L.; Liu, C.; Dorenbos, P.; Tao, Y.; Huang, Y.; Liang, H. Insight into Eu Redox and Pr³⁺ 5d Emission in KSrPO₄ by VRBE Scheme Construction. *Dalton Trans.* **2018**, *47*, 306-313.

(21) Govind, B. N.; Swart, H. C.; Dhoble, S. J. Analysis of the Electron-Vibrational Interaction in the 5d states of Eu²⁺ Ions in LiSrPO₄ Host Matrix. *J. Lumin.* **2019**, *214*, 116564.


- (22) Coelho, A. A. *TOPAS academic, Version 4*; Coelho Software: Brisbane, Australia, **2007**.
- (23) Xia, Z.; Xu, Z.; Chen, M.; Liu, Q. Recent Developments in the New Inorganic Solid-State LED Phosphors. *Dalton Trans.* **2016**, *45*, 11214-11232.
- (24) Ueda, J.; Dorenbos, P.; Bos, A. J. J.; Meijerink, A.; Tanabe, S.; Insight into the Thermal Quenching Mechanism for $\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ce}^{3+}$ through Thermoluminescence Excitation Spectroscopy. *J. Phys. Chem. C* **2015**, *119*, 25003-25008.
- (25) Dorenbos, P. Relation Between Eu^{2+} and Ce^{3+} f \leftrightarrow d-Transition Energies in Inorganic Compounds. *J. Phys.: Condens. Matter.* **2003**, *15*, 4797-4807.
- (26) Lin, C.; Xiao, Z.; Guo, G.; Chan, T.; Liu, R. Versatile Phosphate Phosphors ABPO_4 in White Light-Emitting Diodes: Collocated Characteristic Analysis and Theoretical Calculations. *J. Am. Chem. Soc.* **2010**, *132*, 3020-3028.
- (27) Nair, G. B.; Bhojar, P. D.; Dhoble, S. J. Exploration of Electron-Vibrational Interaction in the 5d states of Eu^{2+} Ions in ABaPO_4 (A = Li, Na, K and Rb) Phosphors. *Luminescence* **2017**, *32*, 22-29.
- (28) Wang, D.; Liu, W.; Zhang, Z. Emission Tuning Studies in $\text{BaMgSiO}_4:\text{RE}$ (RE = Eu^{2+} , Sr^{2+}) for White LEDs. *Mater. Chem. Phys.* **2018**, *207*, 479-488.
- (29) Liu, X.; Xie, W.; Lü, Y.; Feng, J.; Tang, X.; Lin, J.; Dai, Y.; Xie, Y.; Yan, Y. Multichannel Luminescence Properties of Mixed-Valent $\text{Eu}^{2+}/\text{Eu}^{3+}$ Coactivated SrAl_3BO_7 Nanocrystalline Phosphors for Near-UV LEDs. *Inorg. Chem.* **2017**, *56*, 13829-13841.

- (30) Lin, L.; Shi, R.; Zhou, R.; Peng, Q.; Liu, C.; Tao, Y.; Huang, Y.; Dorenbos, P.; Liang, H. The Effect of Sr^{2+} on Luminescence of Ce^{3+} -Doped $(\text{Ca}, \text{Sr})_2\text{Al}_2\text{SiO}_7$. *Inorg. Chem.* **2017**, *56*, 12476-12484.
- (31) Nazarov, M.; Tsukerblat, B.; Noh, D. Vibronic Coupling Parameters and Stokes Shift in Thiogallate Phosphors. *J. Phys. Chem. Solids.* **2008**, *69*, 2605-2612.
- (32) Shannon, R. D. Revised Effective Ionic Radii and Systematic Studies of Interatomic Distances in Halides and Chalcogenides. *Acta Crystallogr., Sect. A: Cryst. Phys., Diffr., Theor. Gen. Crystallogr.* **1976**, *32*, 751-767.
- (33) Wu, Z.; Fu, H.; Liu, J.; Kuang, S.; Wu, M.; Xu, J.; Kuang, X. Synthesis, Crystal Structure and Photoluminescence Properties of New Blue-Green $\text{Ba}_{1-x}(\text{PO}_3)_2: \text{Eu}_x^{2+}$ ($0 < x \leq 0.040$) Phosphors for Near Ultraviolet Based White Light-Emitting Diodes. *RSC Adv.* **2015**, *5*, 42714-42720.
- (34) Qiao, J.; Ning, L.; Molocheev, M. S.; Chuang, Y.; Liu, Q.; Xia, Z. Eu^{2+} Site Preferences in the Mixed Cation $\text{K}_2\text{BaCa}(\text{PO}_4)_2$ and Thermally Stable Luminescence. *J. Am. Chem. Soc.* **2018**, *140*, 9730-9736.
- (35) Zhou, R.; Liu, C.; Lin, L.; Huang, Y.; Liang, H. Multi-Site Occupancies of Eu^{2+} in $\text{Ca}_6\text{BaP}_4\text{O}_{17}$ and Their Potential Optical Thermometric Applications. *Chem. Eng. J.* **2019**, *369*, 376-385.
- (36) Mart ́n, I. R.; Rodr ́guez, V. D.; Rodr ́guez-Mendoza, U. R.; Lav ́n, V. Energy Transfer with Migration. Generalization of the Yokota-Tanimoto Model for Any Kind of Multipole Interaction. *J. Chem. Phys.* **1999**, *111*, 1191-1194.

(37) Georgescu, S.; Voiculescu, A. M.; Matei, C.; Stefan, A.; Toma, O.; Birjega, R. Upconversion Luminescence in Langatate Ceramics Doped with Tm^{3+} and Yb^{3+} . *J. Lumin.* **2014**, *154*, 74-79.

(38) Liu, C.; Qi, Z.; Ma, C.; Dorenbos, P.; Hou, D.; Zhang, S.; Kuang, X.; Zhang, J.; Liang, H. High Light Yield of $\text{Sr}_8(\text{Si}_4\text{O}_{12})\text{Cl}_8: \text{Eu}^{2+}$ under X-ray Excitation and Its Temperature-Dependent Luminescence Characteristics. *Chem. Mater.* **2014**, *26*, 3709-3715.

For Table of Contents Only



Eu^{2+} shows a doublet emission band in RbBaPO_4 under the excitation of UV light and X-ray because of its occupancies in Ba^{2+} and Rb^+ sites. The analyses of electron-vibrational interaction and energy transfer dynamics are applied to get insight into the luminescence properties of Eu^{2+} in Ba^{2+} and Rb^+ sites. The $\text{RbBa}_{0.995}\text{Eu}_{0.005}\text{PO}_4$ phosphor shows potential application in X-ray detection with the light yield of ~ 17700 ph/MeV.