

Data on the surface morphology of additively manufactured Ti-6Al-4V implants during processing by plasma electrolytic oxidation

van Hengel, Ingmar A.J.; Riool, Martijn; Fratila-Apachitei, Lidy E.; Witte-Bouma, Janneke; Farrell, Eric; Zadpoor, Amir A.; Zaat, Sebastian A.J.; Apachitei, Julian

DOI

10.1016/j.dib.2017.06.015

Publication date 2017

Document VersionFinal published version

Published in Data in Brief

Citation (APA)

van Hengel, I. A. J., Riool, M., Fratila-Apachitei, L. E., Witte-Bouma, J., Farrell, E., Zadpoor, A. A., Zaat, S. A. J., & Apachitei, J. (2017). Data on the surface morphology of additively manufactured Ti-6Al-4V implants during processing by plasma electrolytic oxidation. *Data in Brief*, *13*, 385-389. https://doi.org/10.1016/j.dib.2017.06.015

Important note

To cite this publication, please use the final published version (if applicable). Please check the document version above.

Copyright

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights. We will remove access to the work immediately and investigate your claim.



Contents lists available at ScienceDirect

Data in Brief





Data Article

Data on the surface morphology of additively manufactured Ti-6Al-4V implants during processing by plasma electrolytic oxidation



Ingmar A.J. van Hengel ^{a,b,*}, Martijn Riool ^c, Lidy E. Fratila-Apachitei ^{a,b}, Janneke Witte-Bouma ^d, Eric Farrell ^d, Amir A. Zadpoor ^{a,b}, Sebastian A.J. Zaat ^c, Iulian Apachitei ^{a,b,*}

ARTICLE INFO

Article history: Received 28 February 2017 Received in revised form 8 May 2017 Accepted 6 June 2017 Available online 9 June 2017

Keywords: Additive manufacturing Plasma electrolytic oxidation Surface morphology Ti-6Al-4V implants

ABSTRACT

Additively manufactured Ti-6Al-4V implants were biofunctionalized using plasma electrolytic oxidation. At various time points during this process scanning electron microscopy imaging was performed to analyze the surface morphology (van Hengel et al., 2017) [1]. This data shows the changes in surface morphology during plasma electrolytic oxidation. Data presented in this article are related to the research article "Selective laser melting porous metallic implants with immobilized silver nanoparticles kill and prevent biofilm formation by methicillin-resistant Staphylococcus aureus" (van Hengel et al., 2017) [1].

© 2017 The Authors. Published by Elsevier Inc. This is an open access article under the CC BY license

(http://creativecommons.org/licenses/by/4.0/).

^a Department of Biomechanical Engineering, Faculty of Mechanical, Maritime, and Materials Engineering, Delft University of Technology (TU Delft), Mekelweg 2, 2628 CD Delft, The Netherlands

^b Additive Manufacturing Lab, Faculty of Mechanical, Maritime, and Materials Engineering, Delft University of Technology (TU Delft), Mekelweg 2, 2628 CD Delft, The Netherlands

^c Department of Medical Microbiology, Center for Infection and Immunity Amsterdam (CINIMA), Academic Medical Center, University of Amsterdam, Meibergdreef 9, 1105 AZ Amsterdam, The Netherlands

^d Department of Oral and Maxillofacial Surgery, Special Dental Care and Orthodontics, Erasmus MC, University Medical Centre, Wytemaweg 80, 3015 CN Rotterdam, The Netherlands

DOI of original article: http://dx.doi.org/10.1016/j.biomaterials.2017.02.030

^{*}Corresponding authors at: Department of Biomechanical Engineering, Faculty of Mechanical, Maritime, and Materials Engineering, Delft University of Technology (TU Delft), Mekelweg 2, 2628 CD Delft, The Netherlands.

E-mail addresses: I.A.I.vanHengel@tudelft.nl (I.A.I. van Hengel), i.apachitei@tudelft.nl (I. Apachitei).

Specifications Table

Subject area More specific subject area	Material Science Engineering Surface biofunctionalization
Type of data	Microscopy images
How data was acquired	Scanning electron microscope
Data format	Raw
Experimental factors	Ti-6Al-4V implants were fabricated with selective laser melting. Plasma electrolytic oxidation was performed on a custom-made laboratory setup.
Experimental features	Scanning electron microscopy was performed on the surfaces of Ti-6Al-4V implants at various time points during plasma electrolytic oxidation to show the changes in surface morphology.
Data source location Data accessibility	Department of Biomechanical Engineering, Faculty of Mechanical, Maritime, and Materials Engineering, Delft University of Technology (TU Delft) Data is within this article

Value of the data

- Data show the changes in surface morphology of additively manufactured Ti-6Al-4V biomaterials during the plasma electrolytic oxidation process.
- The presented data may be used to compare additively manufactured biomaterials with conventionally produced biomaterials after biofunctionalization by plasma electrolytic oxidation.
- Data may be used to compare the effect of plasma electrolytic oxidation treatment with other biofunctionalization techniques on the surface morphology of additively manufactured Ti-6Al-4V biomaterials.

1. Data

Ti-6Al-4V implants were synthesized by selective laser melting and subsequently biofunctionalized using the electrochemical plasma electrolytic oxidation process. Scanning electron microscopy was performed at various time points from 0 to 300 s during plasma electrolytic oxidation and is presented in Figs. 1–3. The provided data are part of the experimental results in previous work by the authors [1].

2. Experimental design, materials and methods

Ti-6Al-4V implants were manufactured using a selective laser melting printer (SLM-125, Realizer, Borchem, Germany). Specimens were produced from medical grade (grade 23, ELI) Ti-6Al-4V powder (AP&C, Boisbriand, Quebec, Canada) with particle size between 10 and 45 μm and spherical particle morphology. Process parameters were 400 W laser source, layer thickness of 50 μm , laser spot size of 145 μm , layer thickness of 50 μm and exposure time of 300 μs . After selective laser melting, loose powder was removed by vacuum cleaning and samples were thoroughly cleaned by ultrasonication in acetone, 96% ethanol and demineralized water for 5 min subsequently.

Samples were biofunctionalized using plasma electrolytic oxidation on a custom-made laboratory setup. Details regarding the experimental setup can be found in [1]. Plasma electrolytic oxidation is an electrochemical process, which drives uniform growth of the titanium oxide (TiO_2) layer on the surface of titanium biomaterials. The electrolyte contained 0.02 M calcium glycerophosphate and 0.15 M calcium acetate. Plasma electrolytic oxidation was performed for 0–300 s under galvanostatic conditions.




Fig. 1. 200-fold magnification scanning electron microscopy images at different time points of Ti-6Al-4V implants treated with plasma electrolytic oxidation.




Fig. 2. 500-fold magnification scanning electron microscopy images at different time points of Ti-6Al-4V implants treated with plasma electrolytic oxidation.




Fig. 3. 1000-fold magnification scanning electron microscopy images at different time points of Ti-6Al-4V implants treated with plasma electrolytic oxidation.

The surface morphology was analyzed by a scanning electron microscope (JSM-IT100LA, JEOL, Tokyo, Japan). Analysis was performed with beam energies between 5 and 20 kV and a 10 mm working distance. Before analysis, specimens were cleaned for 30 s in acetone and 2-propanol subsequently and coated with a gold layer of 5 ± 2 nm. Imaging was performed at 200, 500 and 1000-fold magnifications (Figs. 1–3).

Transparency document. Supporting information

Transparency data associated with this article can be found in the online version at http://dx.doi. org/10.1016/j.dib.2017.06.015.

Reference

[1] I.A.J. van Hengel, M. Riool, L.E. Fratila-Apachitei, J. Witte-Bouma, E. Farrell, A.A. Zadpoor, S.A.J. Zaat and I. Apachitei, Selective laser melting porous metallic implants with immobilized silver nanoparticles kill and prevent biofilm formation by methicillin-resistant Staphylococcus aureus, Biomaterials 140 (2017) 1-15, http://dx.doi.org/10.1016/j.biomadterials.2017. 02.030.