

Test results

Test: Four point bending test


Samples: Moso (14), Lamboo (23)

Una reunión educativa con el bambu

Robert-Jan Vos TU-Delft


Lamboo

Imperfections: 0




Lamboo

Imperfections: 1






Lamboo

Imperfections: 2



Lamboo

Imperfections: 3



Test results

Test: Four point bending test


Samples: Moso (14), Lamboo (23)

Una reunión educativa con el bambu

Robert-Jan Vos TU-Delft

Moso


Imperfections: 0



MOE

Moso:
Characteristic value:
8620 MPa

Lamboo:
Characteristic value:
8596 MPa



Max. Bending Strength

Lamboo:
Characteristic value:
39.2 MPa

Moso:
Characteristic value:
49.5 MPa

Δ:
Characteristic value:
40.6 MPa

